




THE DATASHEET OF

55.2-SC-18-3





d ±0,1	h ±0,1	Nominal magnetic forces in N		Packaging units	
		SC Sm Co	ND Nd Fe B	SC	ND
4	3	2,5	4	20	20
5	3	3,5	5	20	20
6	3	4	7,5	20	20
8	3	8	13	20	20
10	3	10	15	20	20
12	3	11	20	10	20
15	3	16	28	10	20
18	3	25	35	10	10
20	3	-	42	-	10
24	3	36	55	5	10

Specification

- Materials of the magnet:
 - SmCo
Samarium, cobalt
blank
temperature resistant up to 200 °C
 - NdFeB
Neodymium, iron, boron
nickel-plated
temperature resistant up to 80 °C
- RoHS

On request

- in other dimensions
- made of hard ferrite (HF)

Information

Raw magnets GN 55.2 are unshielded disc-shaped magnets.

Owing to their vast range of different magnet materials and sizes, they are suitable for virtually universal use. They are mostly attached by gluing.

When used without air gap, individual raw magnets always have lower magnetic forces than a magnet system in which shielding and magnetic return enormously intensify the force acting at the adhesion surface. Depending on the air gap between magnet and mating component, individual raw magnets - unlike magnet systems - can have substantially higher magnetic forces.

In the event that no suitable retaining magnets / magnet systems are available, raw magnets may be used in combination with appropriate holding constructions to build up highly specific magnet systems.

see also...

- More information to raw magnets → Page 1380 ff.

How to order	1	Material of the magnet
	2	d
	3	h

GN55.2-ND-24-3

Looking for pricing, stock, or lifecycle information?

Click below to explore more details on WIN SOURCE:

 [View 55.2-SC-18-3 on WIN SOURCE](#)

 [J.W. Winco](#) Information

Optimize Your Supply Chain with WIN SOURCE Solutions

-  Global Sourcing Solution
-  Obsolete Management
-  Cost Control Management
-  Shortage Management
-  Alternative Solution
-  Excess Inventory Management